

# MUTOH Product Bulletin

---

## 13 oz. Mutoh Gloss Scrim Banner

13oz "Gloss" Scrim Banner is a 15-mil 1-sided Vinyl Banner Media. This media has a high tenacity polyester core sandwiched with White Vinyl on both sides. This Banner Media is designed to accept most solvent-based inkjet and UV curable inks used in wide format digital printing systems.

<b>Product Codes</b>	MGSB38	<b>(38" X 150' roll)</b>
	MGSB54	<b>(54" X 150' roll)</b>
	MGSB64	<b>(64" X 150' roll)</b>
<b>Weight</b>	13oz / square yard [FS-191-5041]	
<b>Base Fabric</b>	100% Polyester - Knit [DIN EN ISO 1049-2 / 2060] [9x9 / 1000Dx1000D]	
<b>Tensile Strength</b>	240 lbs x 235 lbs [FS-191-5102 -grab]	
<b>Tear Resistance</b>	75 lbs x 65 lbs [FS-191-5134 -tongue]	
<b>Adhesion</b>	at least 8 lbs / inch [FS-191-5970]	
<b>Temperature Resistance</b>	-22° F ~ 158° F [FS-191-5874]	
<b>U.V. Resistance</b>	Not excessive fading after 1,000 HRS [Weather-O-Meter]	
<b>Flame Resistance</b>	Pass	
<b>Finish</b>	Gloss Finish	

### Recommendations

This media is designed for exterior and interior sign and banner applications. In any exterior application, care should be taken to reinforce hems with webbing and "D" rings attached to the webbing. Grommets should be through the webbing reinforced hems. Fasten securely at all four corners and at grommet points to prevent wind flapping. Wind-whip can cause a banner to self-destruct.

Store in a cool dry area. Prolonged exposure to heat will shorten the shelf life and printability of this media. Standard shelf life is 1 year.

When rolling banners for shipping or storage, care should be taken to make sure the ink has completely cured. Inks not completely cured may re-wet and block.

---

# MUTOH

2602 South 47<sup>th</sup> Street • Phoenix, AZ 85034 • (480) 968.7772 • (800)99.MUTOH • FAX (480)968.7990  
Web Site: [www.mutoh.com](http://www.mutoh.com) • e-mail: [sales@mutoh.com](mailto:sales@mutoh.com)

This information is offered for your general guidance only. It is accurate to the best of our knowledge at the time of printing but is not intended to relieve the user from its' responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to safe handling of this material. Since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied.